

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 0 842 955 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
**22.05.2002 Bulletin 2002/21**

(51) Int Cl.7: **C08F 210/06, C08F 210/08,  
C08L 23/14, C08L 23/12**

(21) Application number: **97120008.4**

(22) Date of filing: **14.11.1997**

**(54) Propylene-1-butene copolymer**

Propylen-1-Buten-Copolymer

Copolymère de propylène-1-butène

(84) Designated Contracting States:  
**BE DE FR GB IT NL**

(30) Priority: **15.11.1996 JP 30451496**

(43) Date of publication of application:  
**20.05.1998 Bulletin 1998/21**

(73) Proprietor: **Sumitomo Chemical Company,  
Limited  
Chuo-ku Osaka 541-8550 (JP)**

(72) Inventors:  
• **Hozumi, Hidetake  
Ichihara-shi, Chiba (JP)**

• **Ijichi, Yasuhito  
Irrington, New York 10533 (US)**

(74) Representative: **VOSSIUS & PARTNER  
Siebertstrasse 4  
81675 München (DE)**

(56) References cited:  
**WO-A-97/44389 US-A- 4 168 361**

• **PATENT ABSTRACTS OF JAPAN vol. 003, no.  
109 (C-058), 12 September 1979 & JP 54 085293  
A (MITSUI PETROCHEM IND LTD), 6 July 1979,**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 0 842 955 B1**

## Description

[0001] The present invention relates to a propylene-1-butene copolymer, and a thermoplastic resin composition. More particularly, it relates to a novel propylene-1-butene copolymer which gives a thermoplastic resin composition having excellent flexibility, tensile elongation characteristics, scratch resistance and transparency when mixing with a resin such as polypropylene, and a thermoplastic resin composition containing said propylene-1-butene copolymer and a polyolefin resin.

[0002] The propylene-1-butene copolymer is used in melt molded articles (e.g. films and sheets) as a soft or semirigid resin material which is superior e.g. in transparency, surface non-tackiness and tensile characteristics. It is blended with a resin such as polypropylene and is also used for improvement of e.g. heat sealability and impact resistance widely.

[0003] U.S. Patent No. 2918457 discloses a propylene-1-butene copolymer produced by using titanium trichloride. Since the propylene-1-butene copolymer has high hardness, when using the propylene-1-butene copolymer for modification of polypropylene, it is effective for improvement of heat sealability and impact resistance, but the flexibility, tensile elongation characteristics and scratch resistance are not improved. Since the propylene-1-butene copolymer contains a low-molecular weight component, there also arose a problem that tackiness is remained on the surface of a molded article.

[0004] JP-A-53-79984, 54-85293, 60-38414, 62-119212 and 62-119213 disclose a propylene-1-butene copolymer containing no low-molecular weight component, and use thereof. Since these propylene-1-butene copolymers have high hardness, when using them for modification of polypropylene, the surface tackiness of the molded article is inhibited and the heat sealability and impact resistance are improved, but the flexibility, tensile elongation characteristics and scratch resistance are not improved.

[0005] JP-A-50-38787 discloses that an amorphous propylene-1-butene copolymer can be obtained by using a titanium trichloride catalyst at 140 to 250°C. When using such a copolymer for modification of polypropylene, the flexibility, tensile elongation characteristics, scratch resistance and transparency are improved, but the properties such as flexibility, tensile elongation characteristics, scratch resistance and transparency are improved only to some extent. These properties could be well improved by using a large amount of propylene-1-butene copolymer, but properties such as strength and heat resistance become worth. Because the said propylene-1-butene copolymer is heterogeneous in composition distribution and molecular weight distribution and shows significant crystallinity, derived from said heterogeneity, flexibility, tensile elongation characteristics, scratch resistance and transparency are improved, but strength and heat resistance are not sufficiently improved.

[0006] A polypropylene thermoplastic resin composition containing propylene-1-butene copolymer, for example, a polypropylene thermoplastic resin composition containing a propylene-1-butenecopolymer which is crystallizable is disclosed in JP-A-8-12719.

[0007] Furthermore, a polypropylene thermoplastic resin composition containing a propylene-1-butene copolymer having a crystallinity of 10 to 30% is disclosed in JP-A-7-42367. However, these propylene-1-butene copolymers have high hardness and the flexibility imparting effect was not recognized in the polypropylene thermoplastic composition containing these propylene-1-butene copolymer.

[0008] It is an object of the invention to provide a propylene-1-butene copolymer, which does not cause the problems as described above. This object could be achieved on the basis of the finding that a novel propylene-1-butene copolymer having a specific Shore A-scale hardness and a specific intrinsic viscosity $[\eta]$  and having neither of a crystalline melting peak and a crystallization peak in case of measuring by a differential scanning calorimeter (DSC), when mixed with a resin such as polypropylene can provide a thermoplastic resin composition having excellent flexibility, tensile elongation characteristics, scratch resistance and transparency.

[0009] Furthermore, it has been found that a polyolefin material using the propylene-1-butene copolymer having a specific Shore A-scale hardness and a specific intrinsic viscosity $[\eta]$  and having neither of a crystalline melting peak and a crystallization peak in case of measuring by a differential scanning calorimeter (DSC) as a modifier is superior in flexibility, tensile elongation characteristics, scratch resistance and transparency.

[0010] That is, the present invention provides a propylene-1-butene copolymer wherein the shore A scale hardness measured according to ASTM D2240 is not more than 70 and the intrinsic viscosity $[\eta]$  measured in a xylene solvent at the temperature of 70°C is not less than 0.3 and the copolymer has neither a crystalline melting peak nor a crystallization peak in case of measuring by a differential scanning calorimeter (DSC).

[0011] The present invention also provides a thermoplastic resin composition comprising 3 to 95% by weight of said propylene-1-butene copolymer and 97 to 5% by weight of a polyolefin resin.

[0012] Regarding the propylene-1-butene copolymer of the present invention, the Shore A-scale hardness measured according to ASTM D2240 is not more than 70, preferably not more than 60. When the hardness is too high, the resulting thermoplastic resin composition is inferior in flexibility.

[0013] Regarding the propylene-1-butene copolymer of the present invention, the intrinsic viscosity $[\eta]$  measured in a xylene solvent at the temperature of 70°C is not less than 0.3, preferably not less than 0.5. When the intrinsic viscosity

is too low, the resulting thermoplastic resin composition is inferior in tensile elongation characteristics.

[0014] The measurement of the intrinsic viscosity  $[\eta]$  is conducted in xylene at 70°C, using an Ubbelohde viscometer. A sample (300 mg) is dissolved in 100 ml of xylene to prepare a solution (3 mg/ml). Furthermore, the solution is diluted in a dilution of 1:2, 1:3 and 1:5 and then measured in a constant-temperature water bath at 70°C(±0.1°C), respectively.

The measurement is repeated three times at each concentration, and the resulting values are used after averaging.

[0015] Regarding the propylene-1-butene copolymer of the present invention, those having neither a crystalline melting peak nor a crystallization peak in case of measuring by a differential scanning calorimeter (DSC) are preferable. When such a condition is not satisfied, the resulting thermoplastic resin composition is inferior in flexibility.

[0016] In heating and cooling processes, the measurement is conducted at a rate of 10°C/minute using a differential scanning calorimeter (DSC220C, manufactured by Seiko Denshi Kogyo Co., Ltd.).

[0017] As the propylene-1-butene copolymer of the present invention, those having a molecular weight distribution (Mw/Mn) measured by gel permeation chromatography (GPC) of not more than 3 are preferable. When the molecular weight distribution is too wide, the stickiness of the thermoplastic resin composition using the copolymer as a modifier may become larger.

[0018] The molecular weight distribution is determined by gel permeation chromatography (GPC) (150C/GPC device, manufactured by Waters Co.). The eluting temperature is 140°C and Sdex Packed Column A-80M is used as a column and, furthermore, polystyrene (manufactured by Toso Co., molecular weight: 68-8,400,000) is used as a molecular weight standard substance. The resulting weight-average molecular weight (Mw) (in terms of polystyrene), number-average molecular weight (Mn) and ratio (Mw/Mn) are taken as the molecular weight distribution. A measuring sample is prepared by dissolving a polymer (about 5 mg) in 5 ml of o-dichlorobenzene in a concentration of about 1 mg/ml. 400  $\mu$ l of the resulting sample solution are injected and the refractive index is detected at a solvent eluting rate of 1.0 ml/min using a refractive index detector.

[0019] Flexibility of the thermoplastic resin composition comprising polyolefine resin and propylene-1-butene copolymer could be controlled arbitrarily by changing the addition amount of copolymer of the present invention. However, from the view point of the property balance such as mechanical strength and heat resistance ability, addition of minimum amount of the propylene-1-butene copolymer is preferable. The flexural modulus of the composition comprising homopolypropylene and propylene-1-butene copolymer of the present invention is preferably less than 2500 kgf/cm<sup>2</sup>, more preferably less than 2300 kgf/cm<sup>2</sup>, most preferably less than 2000 kgf/cm<sup>2</sup> when the composition was obtained by blending homopolypropylene and propylene-1-butene copolymer in the weight ratio of 50/50. When the flexural modulus is out of the above-mentioned range, mechanical strength and heat resistance of the thermoplastic resin may become poor.

[0020] In the present invention, propylene-1-butene copolymer satisfying in the following equation is preferably used.

$$U \leq S \times [(T/100) \times V]^2$$

U: the flexural modulus of the thermoplastic resin composition

S: the flexural modulus of the homopolypropylene

T: content of the homopolypropylene in the thermoplastic resin composition (wt%)

[0021] V is preferably 1.1, more preferably 1.0, further more preferably 0.9, most preferably 0.8. When the flexural modulus of the thermoplastic resin composition is out of the above-mentioned range, balance of mechanical strength and heat resistance may become worth.

[0022] In this case, the propylene-1-butene copolymer satisfying in the following equation is preferably used.

$$W \leq T \times Z$$

T represents content of the homopolypropylene in the thermoplastic resin composition (wt%), W represents scratch depth ( $\mu$ m), wherein Z is preferably 1.0, more preferably 0.9, further more preferably 0.8, most preferably 0.7. Measurement of scratch depth of the composition:

[0023] A scratch mark was made by scratching a press sheet having a thickness of 2 mm at a fixed rate by a scratching needle with a load of 500 g, using a surface properties measuring device Tribogear (manufactured by Shinto Kagaku Co.). The depth of the scratch mark was measured by a contact type surface roughness meter Surfcom (manufactured by Tokyo Seimitsu Co.) in the order of  $\mu$ m.

[0024] When the scratch depth of the thermoplastic resin is out of the above-mentioned range, balance of mechanical strength and heat resistance may become worth.

[0025] The content of 1-butene in the propylene-1-butene copolymer of the present invention is preferably from 0.5

to 90% by mol, more preferably from 1 to 70% by mol. When the content of 1-butene is too small, sufficient improving effect is not obtained sometimes. On the other hand, when the content of 1-butene is too large, the molecular weight of the polymer may be drastically decreased. Also in this case, sufficient improving effect, particularly tensile elongation characteristics of the thermoplastic resin composition, is deteriorated sometimes.

[0026] Regarding the propylene-1-butene copolymer of the present invention, the content of a boiling n-heptane-insoluble matter is preferably not more than 5% by weight, more preferably not more than 3% by weight. When the content of the insoluble matter is too large, the resulting blend composition is inferior in flexibility sometimes.

[0027] Regarding the propylene-1-butene copolymer of the present invention, the content of a boiling methyl acetate-soluble matter is preferably not more than 2% by weight. When the content of the soluble portion is too large, the stickiness of the thermoplastic resin composition using the copolymer as a modifier becomes larger sometimes.


[0028] Regarding the propylene-1-butene copolymer, the arrangement of the propylene and/or 1-butene side chain shows preferably an atactic structure. The fact that the orientation of the side chain of propylene and/or 1-butene shows an atactic structure means the case where the orientation of the side chain of the propylene chain in the copolymer shows an atactic structure, the case where the orientation of the side chain of the 1-butene chain in the copolymer shows an atactic structure, or the case where the orientation of the side chain of the propylene/1-butene combined chain in the copolymer shows an atactic structure. The fact that the propylene-1-butene copolymer of the present invention shows an atactic structure can be confirmed, for example, by the followings. That is, when a homopolypropylene is polymerized by using a transition metal complex used in the polymerization of the propylene-1-butene copolymer of the present invention, the resulting homopolypropylene has a structure that a F(1) value, which is defined by the following equation using each signal intensity [mm], [mr] and [rr] belonging to mm, mr and rr of propylenemethyl carbon decided by  $^{13}\text{C}$  NMR spectrum, is from 40 to 60, preferably from 43 to 57, more preferably from 45 to 55.

$$F(1) = 100 \times [\text{mr}] / ([\text{mm}] + [\text{mr}] + [\text{rr}])$$

[0029] In the similar way, it is possible to confirm that the propylene copolymer of the present invention shows an atactic structure by the fact that a value corresponding to F(1), which is determined by each signal intensity belonging to mm, mr and rr of propylenemethyl carbon, branched methylene carbon of 1-butene and branched terminal methyl carbon of 1-butene, is within the above range. When the propylene-1-butene copolymer does not show an atactic structure, the hardness may be high and the resulting thermoplastic resin composition is inferior in flexibility sometimes. Incidentally, as regards the attribution of mm, mr and rr signals of propylenemethyl carbon, branched methylene carbon of 1-butene and branched terminal methyl carbon of 1-butene it can be referred to T. Asakura, Macromolecules, Vol. 24, page 2334 (1991) and Shinpan Kobunshi Bunseki Hand Book (1995), issued by Kinokuniya Shoten.

[0030] The propylene-1-butene copolymer of the present invention is preferably produced by polymerizing propylene with 1-butene using a catalyst to give a copolymer having neither a crystalline melting peak nor a crystallization peak in case of measuring by a differential scanning calorimeter (DSC).

[0031] As the catalyst, those represented by the following chemical formula [I]:



[ I ]

(wherein  $\text{M}^1$  represents a transition metal atom of Group 4 of the periodic table of the elements; A represents an atom of Group 16 of the periodic table of the elements; B represents an atom of Group 14 of the periodic table of the elements;  $\text{Cp}^1$  represents a group having a cyclopentadiene form anion skeleton;  $\text{X}^1$ ,  $\text{X}^2$ ,  $\text{R}^1$ ,  $\text{R}^2$ ,  $\text{R}^3$ ,  $\text{R}^4$ ,  $\text{R}^5$  and  $\text{R}^6$  independently represent a hydrogen atom, a halogen atom, an alkyl group having 1 to 20 carbon atoms which may be substituted with a halogen atom, an aralkyl group having 7 to 20 carbon atoms which may be substituted with a halogen atom, an aryl group having 6 to 20 carbon atoms which may be substituted with a halogen atom, a substituted silyl group having

[0032] Specific examples of the transition metal complex represented by the chemical formula [I] include transition metal complexes wherein B in the chemical formula [I] is a carbon atom, such as methylene(cyclopentadienyl) (3,5-dimethyl-2-phenoxy) titanium dichloride, methylene(cyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, methylene(cyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, methylene(cyclopentadienyl)(3-phenyl-2-phenoxy)titanium dichloride, methylene(cyclopentadienyl)(3-tert-butylidimethylsilyl-5-methyl-2-phenoxy) titanium dichloride, methylene(cyclopentadienyl)(3-trimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, methylene (cyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, methylene(cyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, methylene(methylcyclopentadienyl) (3,5-dimethyl-2-phenoxy)titanium dichlo- ride, methylene(methylcyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, methylene(methylcyclopenta- dienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, methylene(methylcyclopentadienyl)(3-phenyl-2-phenoxy)ti- tanium dichloride, methylene(methylcyclopentadienyl)(3-tert-butylidimethylsilyl-5-methyl-2-phenoxy)titanium dichlo- ride, methylene(methylcyclopentadienyl)(3-trimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, methylene(methyl- cyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, methylene(methylcyclopentadienyl)(3-tert- butyl-5-chloro-2-phenoxy)titanium dichloride, methylene(tert-butylcyclopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, methylene(tert-butylcyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, methylene(tert-butylcy- clopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, methylene(tert-butylcyclopentadienyl)(3-phenyl- 2-phenoxy)titanium dichloride, methylene(tert-butylcyclopentadienyl)(3-tert-butylidimethylsilyl-5-methyl-2-phenoxy)ti- tanium dichloride, methylene(tert-butylcyclopentadienyl)(3-trimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, methylene(tert-butylcyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, methylene(tert-butylcy- clopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, methylene(tetramethylcyclopentadienyl) (3,5-dimethyl-2-phenoxy)titanium dichloride, methylene(tetramethylcyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, methylene(tetramethylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, methylene (tetramethylcyclopentadienyl)(3-phenyl-2-phenoxy)titanium dichloride, methylene(tetramethylcyclopentadienyl) (3-tert-butylidimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, methylene(tetramethylcyclopentadienyl)(3-trimethyl- silyl-5-methyl-2-phenoxy)titanium dichloride, methylene(tetramethylcyclopentadienyl)(3-tert-butyl-5-methoxy-2-phe- noxy)titanium dichloride, methylene(tetramethylcyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, methylene(trimethylsilylcyclopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, methylene(trimethylsilylcy- clopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, methylene(trimethylsilylcyclopentadienyl)(3-tert-butyl- 5-methyl-2-phenoxy)titanium dichloride, methylene(trimethylsilylcyclopentadienyl)(3-phenyl-2-phenoxy)tita- nium dichloride, methylene(trimethylsilylcyclopentadienyl)(3-tert-butylidimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, methylene(trimethylsilylcyclopentadienyl)(3-trimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, methylene(trimeth- ylsilylcyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, methylene(trimethylsilylcyclopentadi- enyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, methylene(fluorenyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, methylene(fluorenyl)(3-tert-butyl-2-phenoxy)titanium dichloride, methylene(fluorenyl)(3-tert-butyl-5-methyl- 2-phenoxy)titanium dichloride, methylene(fluorenyl)(3-phenyl-2-phenoxy)titanium dichloride, methylene(fluorenyl) (3-tert-butylidimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, methylene(fluorenyl)(3-trimethylsilyl-5-methyl- 2-phenoxy)titanium dichloride, methylene(fluorenyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, methylene (fluorenyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, isopropylidene(cyclopentadienyl)(3,5-dimethyl-2-phe- noxy)titanium dichloride, isopropylidene(cyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, isopropylidene (cyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, isopropylidene(cyclopentadienyl)(3-phenyl- 2-phenoxy)titanium dichloride, isopropylidene(cyclopentadienyl)(3-tert-butylidimethylsilyl-5-methyl-2-phenoxy)titani- um dichloride, isopropylidene(cyclopentadienyl)(3-trimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, isopropyli- dene(cyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, isopropylidene(cyclopentadienyl) (3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, isopropylidene(methylcyclopentadienyl)(3,5-dimethyl-2-phenoxy) titanium dichloride, isopropylidene(methylcyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, isopropylidene (methylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, isopropylidene(methylcyclopentadi- enyl)(3-phenyl-2-phenoxy)titanium dichloride, isopropylidene(methylcyclopentadienyl)(3-tert-butylidimethylsilyl-5-me- thyl-2-phenoxy)titanium dichloride, isopropylidene(methylcyclopentadienyl)(3-trimethylsilyl-5-methyl-2-phenoxy)titani- um dichloride, isopropylidene(methylcyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, isopro- pylidene(methylcyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, isopropylidene(tert-butylcy- clopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, isopropylidene(tert-butylcyclopentadienyl)(3-tert-butyl- 2-phenoxy)titanium dichloride, isopropylidene(tert-butylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, isopropylidene(tert-butylcyclopentadienyl)(3-phenyl-2-phenoxy)titanium dichloride, isopropylidene(tert-but-

[illegible]

(3-tert-butyl-dimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, diphenylmethylene (fluorenyl) (3-trimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, diphenylmethylene (fluorenyl) (3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride and diphenylmethylene (fluorenyl) (3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, compounds wherein titanium of these compounds is replaced by zirconium and hafnium, compounds wherein chloride of these compounds is replaced by bromide, iodide, dimethylamide, diethylamide, n-butoxide and isopropoxide, compounds wherein (cyclopentadienyl) of these compounds is replaced by (dimethylcyclopentadienyl), (trimethylcyclopentadienyl), (n-butylcyclopentadienyl), (tert-butyl-dimethylsilylcyclopentadienyl) and (indenyl), and compounds wherein 3,5-dimethyl-2-phenoxy of these compounds is replaced by 2-phenoxy, 3-methyl-2-phenoxy, 3,5-di-tert-butyl-2-phenoxy, 3-phenyl-5-methyl-2-phenoxy, 3-tert-butyl-dimethylsilyl-2-phenoxy and 3-trimethylsilyl-2-phenoxy; and transition metal complexes wherein B in the chemical formula [I] is an atom of Group 14 of the periodic table of the elements other than a carbon atom such as dimethylsilyl(cyclopentadienyl)(2-phenoxy)titanium dichloride, dimethylsilyl(cyclopentadienyl)(3-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(cyclopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, dimethylsilyl(cyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(cyclopentadienyl)(3,5-di-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(cyclopentadienyl)(5-methyl-3-phenyl-2-phenoxy)titanium dichloride, dimethylsilyl(cyclopentadienyl)(3-tert-butyl-dimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(cyclopentadienyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium dichloride, dimethylsilyl(cyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, dimethylsilyl(cyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, dimethylsilyl(cyclopentadienyl)(3,5-diamyl-2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl)(2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl)(3-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl) (3-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl)(3,5-di-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl)(5-methyl-3-phenyl-2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl)(3-tert-butyl-dimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, dimethylsilyl(methylcyclopentadienyl)(3,5-diamyl-2-phenoxy)titanium dichloride, dimethylsilyl(n-butylcyclopentadienyl)(2-phenoxy)titanium dichloride, dimethylsilyl(n-butylcyclopentadienyl)(3-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(n-butylcyclopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, dimethylsilyl(n-butylcyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(n-butylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(n-butylcyclopentadienyl)(5-methyl-3-phenyl-2-phenoxy)titanium dichloride, dimethylsilyl(n-butylcyclopentadienyl)(3-tert-butyl-dimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(n-butylcyclopentadienyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium dichloride, dimethylsilyl(n-butylcyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, dimethylsilyl(n-butylcyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, dimethylsilyl(n-butylcyclopentadienyl)(3,5-diamyl-2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(3-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(3,5-di-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(5-methyl-3-phenyl-2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(3-tert-butyl-dimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, dimethylsilyl(tert-butylcyclopentadienyl)(3,5-diamyl-2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(3-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(3,5-di-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(5-methyl-3-phenyl-2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(3-tert-butyl-dimethylsilyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, dimethylsilyl(tetramethylcyclopentadienyl)(3,5-diamyl-2-phenoxy)titanium dichloride, dimethylsilyl(trimethylsilylcyclopentadienyl)(2-phenoxy)titanium dichloride, dimethylsilyl(trimethylsilylcyclopentadienyl)(3-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(trimethylsilylcyclopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, dimethylsilyl(trimethylsilylcyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl-

lyl(trimethylsilylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(trimethylsilylcyclopentadienyl)(3,5-di-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(trimethylsilylcyclopentadienyl)(5-methyl-3-phenyl-2-phenoxy)titanium dichloride, dimethylsilyl(trimethylsilylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(trimethylsilylcyclopentadienyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium dichloride, dimethylsilyl(trimethylsilylcyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, dimethylsilyl(trimethylsilylcyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, dimethylsilyl(trimethylsilylcyclopentadienyl)(3,5-diamyl-2-phenoxy)titanium dichloride, dimethylsilyl(indenyl)(2-phenoxy)titanium dichloride, dimethylsilyl(indenyl)(3-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(indenyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, dimethylsilyl(indenyl)(3-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(indenyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(indenyl)(3,5-di-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(indenyl)(5-methyl-3-phenyl-2-phenoxy)titanium dichloride, dimethylsilyl(indenyl)(3-tert-butyl-5-methyl-3-phenyl-2-phenoxy)titanium dichloride, dimethylsilyl(indenyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, dimethylsilyl(indenyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, dimethylsilyl(indenyl)(3,5-diamyl-2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(3-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(3-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(3,5-di-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(5-methyl-3-phenyl-2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(3-tert-butyl-5-methyl-3-phenyl-2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, dimethylsilyl(fluorenyl)(3,5-diamyl-2-phenoxy)titanium dichloride and dimethylsilyl(tetramethylcyclopentadienyl)(1-naphthoxy-2-yl)titanium dichloride, compounds wherein (cyclopentadienyl) of these compounds is replaced by (dimethylcyclopentadienyl), (trimethylcyclopentadienyl), (ethylcyclopentadienyl), (n-propylcyclopentadienyl), (isopropylcyclopentadienyl), (sec-butylcyclopentadienyl), (isobutylcyclopentadienyl), (tert-butylcyclopentadienyl), (phenylcyclopentadienyl), (methylindenyl) and (phenylindenyl), compounds wherein 2-phenoxy of these compounds is replaced by 3-phenyl 2-phenoxy, 3-trimethylsilyl-2-phenoxy and 3-tert-butyl-5-methyl-2-phenoxy, compounds wherein dimethylsilyl of these compounds is replaced by diethylsilyl, diphenylsilyl and dimethoxysilyl, compounds wherein titanium of these compounds is replaced by zirconium and hafnium, and compounds wherein chloride of these compounds is replaced by bromide, iodide, dimethylamide, diethylamide, n-butoxide and isopropoxide. The method of preparing the transition metal complex represented by the chemical formula [I] is disclosed in JP-A-9-87313.

[0033] As the transition metal complex of the present invention, the following compound (A) and/or compound (B) can be used by charging in arbitrary order on polymerization, but the reaction product obtained by previously contacting the combination of arbitrary compounds may be used.

Compound (A): organoaluminum compound

[0034] As the compound (A), known organoaluminum compounds can be used. Preferable examples include any one of (A1) organoaluminum compound represented by the general formula  $E^1_a AlZ_{3-a}$ , (A2) cyclic aluminoxanes having a structure represented by the general formula  $\{-Al(E^2)-O-\}_b$  and (A3) linear aluminoxanes having a structure represented by the general formula  $E^3\{-Al(E^3)-O-\}_c AlE^3_2$  (wherein  $E^1$ ,  $E^2$  and  $E^3$  represent a hydrocarbon group having 1 to 8 carbon atoms, and all of  $E^1$ , all of  $E^2$  and all of  $E^3$  may be the same or different; Z represents hydrogen or halogen, and all of Z may be the same or different; a represents a numeral of 0 to 3; b represents an integer of 2 or more; and c represents an integer of 1 or more) or a mixture of two or more kinds of them.

[0035] Specific examples of the organoaluminum compound (A1) represented by the general formula  $E^1_a AlZ_{3-a}$  include trialkylaluminum such as trimethylaluminum, triethylaluminum, tripropylaluminum, triisobutylaluminum and trihexylaluminum; dialkylaluminum chloride such as dimethylaluminum chloride, diethylaluminum chloride, dipropylaluminum chloride, diisobutylaluminum chloride and dihexylaluminum chloride; alkylaluminum dichloride such as methylaluminum dichloride, ethylaluminum dichloride, propylaluminum dichloride, isobutylaluminum dichloride and hexylaluminum dichloride; and dialkylaluminum hydride such as dimethylaluminum hydride, diethylaluminum hydride, dipropylaluminum hydride, diisobutylaluminum hydride and dihexylaluminum hydride.

[0036] Among them, trialkylaluminum is preferable, and triethylaluminum and triisobutylaluminum are more preferable.

[0037] Specific examples of  $E^2$  and  $E^3$  in the cyclic aluminoxane (A2) having a structure represented by the general formula  $\{-Al(E^2)-O-\}_b$  and linear aluminoxane (A3) having a structure represented by the general formula  $E^3\{-Al(E^3)-O-\}_c AlE^3_2$  include alkyl groups such as methyl group, ethyl group, n-propyl group, isopropyl group, n-butyl group, isobutyl group, n-pentyl group and neopentyl group. b is an integer of 2 or more, and c is an integer of 1 or more. Preferably,  $E^2$  and  $E^3$  are methyl groups or isobutyl groups, b is 2 to 40 and c is 1 to 40.



[0038] The above aluminosilicate is produced by various methods. The method is not specifically limited, and the aluminosilicate may be produced by known methods. For example, it is produced by bringing a solution, prepared by dissolving a trialkylaluminum (e.g. trimethylaluminum) in a suitable solvent (e.g. benzene or aliphatic hydrocarbon) into contact with water. There can also be used a method of bringing a trialkylaluminum (e.g. trimethylaluminum) into contact with a metal salt containing crystallization water (e.g. copper sulfate hydrate).

#### Compound (B)

[0039] As the compound (B), any one of (B1) boron compound represented by the general formula  $BQ^1Q^2Q^3$ , (B2) boron compound represented by the general formula  $G^+(BQ^1Q^2Q^3Q^4)^-$  and (B3) boron compound represented by the general formula  $(L-H)^+(BQ^1Q^2Q^3Q^4)^-$  can be used.

[0040] In the boron compound (B) represented by the general formula  $BQ^1Q^2Q^3$ , B represents a trivalent boron atom in the valence state; and  $Q^1$  to  $Q^3$  may be the same or different and represent a halogen atom, a hydrocarbon group having 1 to 20 carbon atoms, a halogenated hydrocarbon group having 1 to 20 carbon atoms, a substituted silyl group having 1 to 20 carbon atoms, an alkoxy group having 1 to 20 carbon atoms or an amino group having 2 to 20 carbon atoms. Preferably,  $Q^1$  to  $Q^3$  represent a halogen atom, a hydrocarbon group having 1 to 20 carbon atoms or a halogenated hydrocarbon group having 1 to 20 carbon atoms.

[0041] Specific examples of the compound (B1) include tris(pentafluorophenyl)borane, tris(2,3,5,6-tetrafluorophenyl)borane, tris(2,3,4,5-tetrafluorophenyl)borane, tris(3,4,5-trifluorophenyl)borane, tris(2,3,4-trifluorophenyl)borane and phenylbis(pentafluorophenyl)borane. Among them, tris(pentafluorophenyl)borane is most preferable.

[0042] In the boron compound (B2) represented by the general formula  $G^+(BQ^1Q^2Q^3Q^4)^-$ ,  $G^+$  represents an inorganic or organic cation; B represents a trivalent boron in the valence state; and  $Q^1$  to  $Q^4$  are the same as  $Q^1$  to  $Q^3$  in the above (B1).

[0043] In the compound represented by the general formula  $G^+(BQ^1Q^2Q^3Q^4)^-$ , specific examples of  $G^+$  as an inorganic cation include e.g. a ferrocenium cation, alkyl-substituted ferrocenium cation or silver cation, and specific examples of  $G^+$  as an organic cation include a triphenylmethyl cation. Examples of  $(BQ^1Q^2Q^3Q^4)^-$  include tetrakis(pentafluorophenyl)borate, tetrakis(2,3,5,6-tetrafluorophenyl)borate, tetrakis(2,3,4,5-tetrafluorophenyl)borate, tetrakis(3,4,5-trifluorophenyl)borate, tetrakis(2,2,4-trifluorophenyl)borate, phenylbis(pentafluorophenyl)borate and tetrakis(3,5-bis(trifluorophenyl)methyl)borate.

[0044] Examples of the specific combination of them include ferrocenium tetrakis(pentafluorophenyl)borate, 1,1'-dimethylferrocenium tetrakis(pentafluorophenyl)borate, silver tetrakis(pentafluorophenyl)borate, triphenylmethyltetrakis(pentafluorophenyl)borate and triphenylmethyltetrakis(3,5-bis(trifluorophenyl)borate).

[0045] Among them, triphenyltetrakis(pentafluorophenyl)borate is most preferable.

[0046] In the boron compound (B3) represented by the general formula  $(L-H)^+(BQ^1Q^2Q^3Q^4)^-$ ,  $(L-H)^+$  represents a Brønsted acid; B represents a trivalent boron in the valence state; and  $Q^1$  to  $Q^4$  are the same as  $Q^1$  to  $Q^3$  in the above (B1).

[0047] In the compound represented by the general formula  $(L-H)^+(BQ^1Q^2Q^3Q^4)^-$ , specific examples of  $(L-H)^+$  as Brønsted acid include trialkyl-substituted ammonium, N,N-dialkylanilinium, dialkylammonium and triarylphosphonium, and specific examples of  $(BQ^1Q^2Q^3Q^4)^-$  include the same one as that described above.

[0048] Examples of the specific combination of them include triethylammonium tetrakis(pentafluorophenyl)borate, tripropylammonium tetrakis(pentafluorophenyl)borate, tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate, tri(n-butyl)ammonium tetrakis(3,5-bis(trifluorophenyl)borate, N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate, N,N-diethylanilinium tetrakis(pentafluorophenyl)borate, N,N-2,4,6-pentamethylanilinium tetrakis(pentafluorophenyl)borate, N,N-dimethylanilinium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, diisopropylammonium tetrakis(pentafluorophenyl)borate, dicyclohexylammonium tetrakis(pentafluorophenyl)borate, triphenylphosphonium tetrakis(pentafluorophenyl)borate, tri(methylphenyl)phosphonium tetrakis(pentafluorophenyl)borate, tri(dimethylphenyl)phosphonium and tetrakis(pentafluorophenyl)borate. Among them, tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate or N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate is most preferable.

[0049] In the present invention, the transition metal complex represented by the chemical formula [I] and compound (A) and/or compound (B) can be used by charging in arbitrary order on polymerization, but the reaction product obtained by previously contacting the combination of arbitrary compounds may be used.

[0050] It is preferable that each catalyst is used so that the molar ratio of the compound (A) to the transition metal complex is from 0.1 to 10000, more preferably from 5 to 2000, and the molar ratio of the compound (B) to the transition metal complex is from 0.01 to 100, more preferably from 0.5 to 10. A concentration of each catalyst component used in the state of a solution or the state of being suspended in a solvent is appropriately selected according to the performance of the device used for feeding each catalyst component in a polymerization reactor. It is preferable that each component is generally used so that the amount of transition metal complex represented by the chemical formula [I] is normally from 0.01 to 500  $\mu\text{mol/g}$ , preferably from 0.05 to 100  $\mu\text{mol/g}$ , more preferably from 0.05 to 50  $\mu\text{mol/g}$ , the

amount of compound (A) is normally from 0.01 to 10000  $\mu\text{mol/g}$ , preferably from 0.1 to 5000  $\mu\text{mol/g}$ , more preferably from 0.1 to 2000  $\mu\text{mol/g}$ , in terms of Al atom, and the amount of compound (B) is normally from 0.01 to 500  $\mu\text{mol/g}$ , preferably from 0.05 to 200  $\mu\text{mol/g}$ , more preferably from 0.05 to 100  $\mu\text{mol/g}$ .

[0051] As the method of producing the propylene-1-butene copolymer, for example, there can be used solvent polymerization using an aliphatic hydrocarbon (e.g. butane, pentane, hexane, heptane and octane), an aromatic hydrocarbon (e.g. benzene and toluene), or a halogenated hydrocarbon (e.g. methylene dichloride) as a solvent, slurry polymerization and vapor phase polymerization in a gaseous monomer. It is also possible to use both continuous polymerization and batch polymerization. The polymerization temperature is within the range from  $-50$  to  $200^{\circ}\text{C}$ , preferably from  $-20$  to  $100^{\circ}\text{C}$ . The polymerization pressure is preferably from normal pressure to  $60\text{ kg/cm}^2\text{G}$ . The polymerization time is appropriately selected according to the kind of the solvent to be used and reaction device, but is within the range from 1 minute to 20 hours. It is also possible to add chain transfer agents such as hydrogen, so as to adjust the molecular weight of the polymer.

[0052] The thermoplastic resin composition of the present invention comprises 3 to 95% by weight of the above propylene-1-butene copolymer and 97 to 5% by weight of a polyolefin resin.

[0053] Examples of the polyolefin resin include high-density polyethylene, medium-density polyethylene, low-density polyethylene, LLDPE (straight-chain low-density polyethylene), polypropylene resin and poly-4-methylpentene-1. Among them, polypropylene resin is preferable.

[0054] As the polypropylene resin used in the composition, a crystalline polypropylene resin is preferable, and a homopolymer of propylene or a random or block copolymer of propylene and a small amount of  $\alpha$ -olefin is preferable.

When the above polypropylene resin is a random copolymer, the copolymerization proportion of the other  $\alpha$ -olefin in the copolymer is preferably not more than 10% by weight, more preferably from 0.5 to 7% by weight. When the above polypropylene resin is a block copolymer, the copolymerization proportion of the other  $\alpha$ -olefin in the copolymer is preferably from 1 to 40% by weight, more preferably from 1 to 25% by weight, further more preferably from 2 to 20% by weight, most preferably from 3 to 15% by weight. These polypropylene polymers may be those prepared by using two or more polymers in combination thereof. As the index of the crystallizability of polypropylene, for example, melting point or crystalline melting enthalpy may be used. The melting point is preferably within the range from  $120$  to  $176^{\circ}\text{C}$ , and the crystalline melting enthalpy is preferably within the range from  $60$  to  $120\text{ J/g}$ . When the melting point or melting enthalpy of the crystal is too low, the resulting material may be inferior in heat resistance.

[0055] Examples of the method of producing the polyolefin resin include a method of producing a propylene homopolymer, comprising homopolymerizing propylene in a single- or multi-stage according to slurry polymerization, vapor phase polymerization, bulk polymerization, solution polymerization or a combination thereof, using a so-called Ziegler-Natta catalyst using a titanium-containing solid transition metal component in combination with an organometal component or a metallocene catalyst composed of a compound having at least one cyclopentadienyl skeleton of a transition metal of Group 4A to Group 6A of the periodic table and a cocatalyst component, or a method of producing a propylene/ $\alpha$ -olefin copolymer, comprising copolymerizing propylene with  $\alpha$ -olefin having 2 or 4 to 12 carbon atoms, preferably ethylene, in a single- or multi-stage. A commercially available product can also be used.

[0056] The thermoplastic resin composition of the present invention comprises 3 to 95% by weight of the propylene-1-butene copolymer and 97 to 5% by weight of the polyolefin resin ((A) + (B) = 100%). Preferably, the thermoplastic resin composition comprises 10 to 80% by weight of the propylene-1-butene copolymer and 90 to 20% by weight of the polyolefin resin. More preferably, the thermoplastic resin composition comprises 30 to 70% by weight of the propylene-1-butene copolymer and 70 to 30% by weight of the polyolefin resin. When the amount of the propylene-1-butene copolymer is too large (the amount of the polyolefin resin is too small), the fluidity is lowered, which results in poor moldability, strength and heat resistance. On the other hand, when the amount of the propylene-1-butene copolymer is too small (the amount of the polyolefin resin is too large), the flexibility is poor or scratch resistance is poor.

[0057] To the thermoplastic resin composition containing the propylene-1-butene copolymer of the present invention, other rubber components such as ethylene-propylene copolymer rubber, ethylene-propylene-nonconjugated diene copolymer rubber, ethylene-1-butene copolymer rubber, polybutadiene, styrene-butadiene block copolymer rubber, styrene-butadiene-styrene block copolymer rubber, styrene-butadiene random copolymer rubber, partially hydrogenated styrene-butadiene-styrene block copolymer rubber, partially hydrogenated styrene-butadiene random copolymer rubber, styrene-isoprene block copolymer rubber and partially hydrogenated styrene-isoprene block copolymer rubber may be added, if necessary, in addition to the propylene-1-butene copolymer and polyolefin resin as the essential component. The crosslinking reaction can also be conducted by the addition of peroxides, if necessary. Furthermore, antioxidants, heat stabilizers, ultraviolet absorbers, lubricants, antistatic agents, pigments, fillers and/or flame retardants may also be added, if necessary.

[0058] Examples of the method of obtaining the thermoplastic resin composition containing the propylene-1-butene copolymer of the present invention include method of melt-kneading the respective components, using a twin-screw extruder or a Banbury mixer.

[0059] The thermoplastic resin composition containing the propylene-1-butene copolymer of the present invention

can be suitably used e.g. in appliances, automobile parts and notions, utilizing its excellent characteristics. In the automobile parts, it can be suitably used in interior skins such as in-pane, door and pillar, as well as air-bag cover.

#### EXAMPLES

[0060] The present invention will now be illustrated by means of the following Examples, which should not be construed as a limitation of the scope of the invention.

[0061] The measuring method of the content of 1-butene in the propylene-1-butene copolymer is as follows.

#### [Calibration curve]

[0062] Each mixture of propylene and 1-butene homopolymers in various mixing ratios was heat-pressed and then molded into a film having a thickness of 0.05 mm. Using an infrared spectrometer, an absorbance ratio of a peak derived from a propylene unit (wavenumber:  $1150\text{ cm}^{-1}$ ) to a peak derived from a 1-butene unit (wavenumber:  $770\text{ cm}^{-1}$ ) was determined and the content of the 1-butene unit in the mixture was plotted versus this absorbance ratio. A regression line was determined from these plots and was taken as a calibration curve. Incidentally, the mixture of the propylene and 1-butene homopolymers was dissolved in toluene and methanol was added, and the resulting precipitate was used after drying.

#### [Measurement of content of 1-butene]

[0063] The propylene-1-butene copolymer was heat-pressed and molded into a film having a thickness of 0.05 mm. Then, an absorbance ratio of a peak derived from a propylene unit to a peak derived from a 1-butene unit was determined and the content of the 1-butene unit in the propylene-1-butene copolymer was calculated by the calibration curve obtained by the above method.

[0064] The hardness of the propylene-1-butene copolymer was measured according to ASTM D2240.

[0065] In heating and cooling processes, the measurement was conducted at a rate of  $10\text{ }^{\circ}\text{C}/\text{minute}$  using a differential scanning calorimeter (DSC220C, manufactured by Seiko Denshi Kogyo Co.).

[0066] The measurement of the intrinsic viscosity  $[\eta]$  was conducted in xylene at  $70^{\circ}\text{C}$  using an Ubbelohde viscometer. A sample (300 mg) was dissolved in 100 ml of xylene to prepare a solution (3 mg/ml). Furthermore, the solution was diluted in a dilution of 1:2, 1:3 and 1:5 and then measured in a constant-temperature water bath at  $70^{\circ}\text{C}(\pm 0.1^{\circ}\text{C})$ , respectively. The measurement was repeated three times at each concentration, and the resulting values are used after averaging.

[0067] The molecular weight distribution was determined by gel permeation chromatography (GPC) (150C/GPC device, manufactured by Waters Co.). The eluting temperature was  $140^{\circ}\text{C}$  and Sdex Packed Column A-80M was used as a column and, furthermore, polystyrene (manufactured by Toso Co., molecular weight: 68-8,400,000) was used as a molecular weight standard substance. The resulting weight-average molecular weight (Mw) (in terms of polystyrene), number-average molecular weight (Mn) and ratio (Mw/Mn) were taken as the molecular weight distribution. A measuring sample was prepared by dissolving a polymer (about 5 mg) in 5 ml of o-dichlorobenzene in a concentration of about 1 mg/ml. 400  $\mu\text{l}$  of the resulting sample solution were injected and the refractive index is detected at a solvent eluting rate of 1.0 ml/min using a refractive index detector. Using a twin-screw batch type laboplasto-mill (manufactured by Toyo Seiki Co.), the formulation components shown in Table 2 were kneaded at the temperature of  $200^{\circ}\text{C}$ , at a screw rotary speed of 100 rpm for 3 minutes. The composition was pressed at  $200^{\circ}\text{C}$  to prepare a sheet having a thickness of 2 mm. A test sample was punched out from the press sheet and then measured.

[0068] Various characteristics of the propylene-1-butene copolymer compositions described in the Examples and Comparative Examples were measured by the following methods.

(1) Hardness: ASTM D2240

(2) Bending test: JIS K7203

(3) Tensile test: JIS K6301 The test was conducted at a stress rate of 200 (mm/min.) using a No. 3 dumbbell.

(4) Scratch resistance test: A scratch mark was made by scratching a press sheet having a thickness of 2 mm as a sample at a fixed rate by a scratching needle with a load of 500 g, using a surface properties measuring device Tribogear (manufactured by Shinto Kagaku Co.). The depth of the scratch mark was measured by a contact type surface roughness meter Surfcom (manufactured by Tokyo Seimitsu Co.) in the order of  $\mu\text{m}$ .

(5) Haze: JIS K7105 A press sheet having a thickness of 2 mm was measured.

(6) Differential scanning calorimeter (DSC): In heating and cooling processes, the measurement was conducted at a rate of  $10^{\circ}\text{C}/\text{minute}$  using a differential scanning calorimeter (DSC220C, manufactured by Seiko Denshi Kogyo Co.).

## EP 0 842 955 B1

### Example 1

5 [0069] After a separable flask reactor having a volume of 2 l was equipped with a stirrer, a thermometer, a dropping funnel and a reflux condenser and evacuated, the atmosphere in the flask was replaced by nitrogen. Toluene (1 liter) was introduced into the flask as a polymerization solvent. Then, propylene (8 NL/min.) and 1-butene (0.5 NL/min.) were continuously fed into the flask, and the solvent temperature invention have low flexural modulus, high tensile elongation and excellent scratch resistance and transparency in comparison with the polypropylene compositions of Comparative Examples 6 to 10 using the copolymers of Comparative Example 1 to 5.

10

15

20

25

30

35

40

45

50

55

&lt;Table 1&gt;

Propylene-1-butene copolymer

	Example							
	1	2	3	4	5	6	7	8
	A-1 PBR	A-2 PBR	A-3 PBR	A-4 PBR	A-5 PBR	A-6 PBR	A-7 PBR	A-8 PBR
Polymerization temperature	30	30	30	30	30	30	30	30
Polymerization time	30	30	30	30	30	30	30	30
Propylene gas	8	6	8	4	8	8	8	8
1-Butene gas	0.1	0.1	0.2	0.1	0.3	0.5	0.5	0.5
Hydrogen gas	0	0	0	0	0	0	0	3
* 1 (a)	1.25	1.25	1.25	1.25	1.25	1.25	0.75	1.25
* 2 (b)	0.025	0.025	0.025	0.025	0.025	0.025	0.0075	0.025
* 3 (c)	0.005	0.005	0.005	0.005	0.005	0.005	0.0015	0.005
Propylene content	>99.5	98	93	92	88	81	57	81
1-Butene content	<0.5	2	7	8	12	19	43	19
Hardness:								
Shore A-scale	45	46	45	45	45	34	24	13
Shore D-scale	12	13	12	12	13	8	5	-
Intrinsic viscosity [ $\eta$ ]	2.1	1.7	1.5	1.4	1.3	1.0	0.5	0.4
Tg	-7.4	-7.2	-7.7	-7.9	-8.2	-9.3	-14.2	-8.5
Crystallizability	No	No	No	No	No	No	No	No
Crystalline melting point	No	No	No	No	No	No	No	No
Crystalline melting calorific	No	No	No	No	No	No	No	No
GPC Mw/Mn	2.5	2.4	2.2	2.2	2.2	2.1	2.1	2.7

&lt;Table 2&gt;

		Comparative example				
		1	2	3	4	5
		A-9 PB	A-10 PBR	A-11 PBR	A-12 PBR	A-13 PP
Polymerization temperature	°C	-	-	30	50	30
Polymerization time	min	-	-	30	30	30
Propylene gas	L/min	-	-	8	8	8
1-Butene gas	L/min	-	-	1.0	0.5	0
Hydrogen gas	L/min	-	-	0	3	0.7
* 1 (a)	mmol	-	-	1.25	1.25	0.625
* 2 (b)	mmol	-	-	0.01	0.025	0.0125
* 3 (c)	mmol	-	-	-	0.005	0.0025
* 4 (d)	mmol	-	-	0.02	-	-
Propylene content	mol%	24	71	70	79	100
1-Butene content	mol%	76	29	30	21	0
Hardness:						
Shore A-scale		94	39	93	<10	40
Shore D-scale		47	12	52	-	-
Intrinsic viscosity [ $\eta$ ]	dl/g	1.4	0.4	1.8	0.2	1.1
T <sub>g</sub>	°C	-27	-18.4	-12.1	-10.3	-6.5
Crystallizability		Yes	Yes	Yes	No	No
Crystalline melting point	°C	75	49.7	76.2	No	No
Crystalline melting calorific	kJ/mg	27	4	30	No	No
GPC Mw/Mn		3.7	8.8	2.2	2.3	3.2

&lt;Table 2&gt;

Propylene-1-butene copolymer

1(a): Triisobutylaluminum

5 \*2(b): Triphenylmethylnetrakis(pentafluorophenyl)borate

10 \*3(c): Dimethylsilyl(tetramethylcyclopentadienyl)(3-t-butyl-5-methyl-2-phenoxy)titanium dichloride

15 \*4(d): A-8PB: Polybutene M2481 (manufactured by Mitsui Petrochemical Co.), MI at 230°C under load of 2.16 Kg: 4.0  
A-9PBR: Propylene-1-butene rubber UBETAC APAO UT2780  
(manufactured by UBE REXENE Co.)

20 [0070] A-1 to A-8, A-9 to A-12 PBR are propylene-1-butene rubbers.

&lt;Table 3&gt;

propylene-1-butene copolymer composition

Copolymer	Unit	Example								
		9	10	11	12	13	14	15	16	
A-1	wt%	50	50	50	50	50	50	50	50	
A-2	wt%									
A-3	wt%									
A-4	wt%									
A-5	wt%									
A-6	wt%									
A-7	wt%									
A-8	wt%									
B-1	wt%	50	50	50	50	50	50	50	50	
Hardness: Shore A-scale Shore D-scale Flexural modulus Tensile strength Tensile elongation Scratch depth (500 g load) Haze (2 mm) PP crystalline melting calorie	Kgf/cm <sup>2</sup>	93	93	93	93	93	93	93	-	
	Kgf/cm <sup>2</sup>	52	53	52	52	53	52	52	-	
	%	1350	1330	1340	1450	1440	1420	1420	1400	
	%	106	122	129	121	124	111	101	108	
	μm	870	1000	980	900	960	860	680	700	
	%	22	19	27	25	21	35	46	64	
	%	80	69	66	68	70	70	67	70	
	mj/mg	56	55	57	58	54	54	55	44	



&lt;Table 4&gt;

Propylene-1-butene copolymer composition


Copolymer	Unit	Comparative example				
		6	7	8	9	10
A-9	wt%	50	50	50	37	50
A-10	wt%					
A-11	wt%					
A-12	wt%					
A-13	wt%					
B-1	wt%	50	50	50	63	50
Hardness:						
Shore A-scale		97	92	-	-	92
Shore D-scale		63	53	-	-	51
Flexural modulus		6740	2560	6800	2720	1610
Tensile strength	Kgf/cm <sup>2</sup>	258	152	300	109	76
Tensile elongation	%	400	720	680	470	393
Scratch depth (500 g load)	$\mu$ m	83	75	48	79	33
Haze (2 mm)	%	86	71	87	79	84
PP crystalline melting	mj/mg	49 +	56	38	53	44
calorie		8.8*				

B-1: Homopolypropylene wherein MI at 230°C under a load of 2.16 Kg is 14 (g/10 min.)

\*: Melting calorie peak which arises between Tm of polypropylene and that of polybutene

## Claims

1. A propylene-1-butene copolymer wherein the Shore A-scale hardness measured according to ASTM D2240 is not more than 70 and the intrinsic viscosity  $[\eta]$  measured in a xylene solvent at the temperature of 70°C is not less than 0.3 and which shows no crystalline melting peak and no crystallization peak in differential scanning calorimeter (DSC) measurement.
2. The propylene-1-butene copolymer according to claim 1, wherein the Shore A-scale hardness measured according to ASTM D2240 is not more than 60.
3. The propylene-1-butene copolymer according to claim 1 or 2, wherein the intrinsic viscosity  $[\eta]$  measured in a xylene solvent at the temperature of 70°C is not less than 0.5.
4. The propylene-1-butene copolymer according to any one of claims 1 to 3, wherein the flexural modulus of the thermoplastic resin composition comprising 50% weight of the propylene-1-butene copolymer and 50% weight of the homopolypropylene is less than 2500 kgf/cm<sup>2</sup>.
5. The propylene-1-butene copolymer according to any one of claims 1 to 4, wherein the molecular weight distribution Mw/Mn measured by gel permeation chromatography (GPC) is not more than 3.
6. The propylene-1-butene copolymer according to any one of claims 1 to 5, wherein the content of 1-butene is from 0.5 to 90% by mol, preferably from 1 to 70% by mol.
7. The propylene-1-butene copolymer according to any one of claims 1 to 6, wherein the content of a boiling n-heptane-insoluble component is not more than 5% by weight, preferably not more than 3% by weight.
8. The propylene-1-butene copolymer according to any one of claims 1 to 7, wherein the content of a boiling methyl acetate-soluble component is not more than 2% by weight.
9. The propylene-1-butene copolymer according to any one of claims 1 to 8, wherein said copolymer is obtained by copolymerizing propylene with 1-butene using a catalyst which can produce a propylene polymer having neither a crystalline melting peak nor a crystallization peak in case of measuring by a differential scanning calorimeter (DSC).
10. The propylene-1-butene copolymer according to claim 9, wherein the catalyst is represented by the following chemical formula (I):



[ I ]

(wherein M<sup>1</sup> represents a transition metal atom of Group 4 of the periodic table of the elements; A represents an atom of Group 16 of the periodic table of the elements; B represents an atom of Group 14 of the periodic table of the elements; Cp<sup>1</sup> represents a group having a cyclopentadiene form anion skeleton; X<sup>1</sup>, X<sup>2</sup>, R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup> and R<sup>6</sup> independently represent a hydrogen atom, a halogen atom, an alkyl group having 1 to 20 carbon atoms which may be substituted with a halogen atom, an aralkyl group having 7 to 20 carbon atoms which may be sub-

stituted with a halogen atom, an aryl group having 6 to 20 carbon atoms which may be substituted with a halogen atom, a substituted silyl group having 1 to 20 carbon atoms which may be substituted with a halogen atom, an alkoxy group having 1 to 20 carbon atoms which may be substituted with a halogen atom, an aralkyloxy group having 7 to 20 carbon atoms which may be substituted with a halogen atom, an aryloxy group having 6 to 20 carbon atoms which may be substituted with a halogen atom, or a di-substituted amino group having 2 to 20 carbon atoms, R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup> and R<sup>6</sup> may optionally be combined with each other to form a ring).

11. A thermoplastic resin composition comprising 3 to 95% by weight, preferably 10 to 80% by weight of the propylene-1-butene copolymer according to claim 1 and 97 to 5% by weight preferably 90 to 20% by weight of a polyolefin resin.

12. The thermoplastic resin composition according to claim 11, wherein the polyolefin resin is a crystalline polypropylene resin.

13. Use of the thermoplastic resin composition according to claims 11 or 12 for the production of formed articles.

#### Patentansprüche

1. Propylen-1-Buten-Copolymer, bei dem die gemäß ASTM D2240 gemessene Shore-Härte der Skala A nicht höher als 70 und die in einem Xylollösungsmittel bei einer Temperatur von 70°C gemessene Grenzviskosität [ $\eta$ ] nicht niedriger als 0,3 ist, und das keinen Kristallschmelzpeak und keinen Kristallisationspeak bei der Differentialscanningkalorimetrie (DSK) zeigt.

2. Propylen-1-Buten-Copolymer gemäß Anspruch 1, bei dem die gemäß ASTM D2240 gemessene Shore-Härte der Skala A nicht höher ist als 60.

3. Propylen-1-Buten-Copolymer gemäß Anspruch 1 oder 2, bei dem die in einem Xylollösungsmittel bei einer Temperatur von 70°C gemessene Grenzviskosität [ $\eta$ ] nicht niedriger als 0,5 ist.

4. Propylen-1-Buten-Copolymer gemäß einem der Ansprüche 1 bis 3, bei dem das Biegemodul der thermoplastischen Harzzusammensetzung, umfassend 50 Gewichts-% Propylen-1-Buten-Copolymer und 50 Gewichts-% Homopolypropylen, niedriger als 2500 kgf/cm<sup>2</sup> ist.

5. Propylen-1-Buten-Copolymer gemäß einem der Ansprüche 1 bis 4, bei dem die durch Gelpermeationschromatographie (GPC) gemessene Molekulargewichtsverteilung Mw/Mn nicht höher als 3 ist.


6. Propylen-1-Buten-Copolymer gemäß einem der Ansprüche 1 bis 5, bei dem der Gehalt an 1-Buten 0,5 bis 90 mol-%, vorzugsweise 1 bis 70 mol-% beträgt.

7. Propylen-1-Buten-Copolymer gemäß einem der Ansprüche 1 bis 6, bei dem der Gehalt eines in siedendem n-Heptan unlöslichen Bestandteils nicht höher als 5 Gewichts-%, vorzugsweise nicht höher als 3 Gewichts-% ist.

8. Propylen-1-Buten-Copolymer gemäß einem der Ansprüche 1 bis 7, bei dem der Gehalt eines in siedendem Methylacetat löslichen Bestandteils nicht höher als 2 Gewichts-% ist.

9. Propylen-1-Buten-Copolymer gemäß einem der Ansprüche 1 bis 8, bei dem das Copolymer durch Copolymerisieren von Propylen mit 1-Buten unter Verwendung eines Katalysators erhalten worden ist, der ein Propylenpolymer erzeugen kann, das weder einen Kristallschmelzpeak noch einen Kristallisationspeak im Falle einer Messung durch ein Differentialscanningkalorimeter (DSK) aufweist.

10. Propylen-1-Buten-Copolymer gemäß Anspruch 9, bei dem der Katalysator die folgende chemische Formel (I) aufweist:



[ I ]

(wobei M<sup>1</sup> ein Übergangsmetallatom der Gruppe 4 des Periodensystems der Elemente darstellt, A ein Atom der Gruppe 16 des Periodensystems der Elemente darstellt, B ein Atom der Gruppe 14 des Periodensystems der Elemente darstellt, Cp<sup>1</sup> eine Gruppe mit einem anionischen Cyclopentadiengerüst darstellt, X<sup>1</sup>, X<sup>2</sup>, R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup> und R<sup>6</sup> unabhängig voneinander ein Wasserstoffatom, ein Halogenatom, einen Alkylrest mit 1 bis 20 Kohlenstoffatomen, der mit einem Halogenatom substituiert sein kann, einen Aralkylrest mit 7 bis 20 Kohlenstoffatomen, der mit einem Halogenatom substituiert sein kann, einen Arylrest mit 6 bis 20 Kohlenstoffatomen, der mit einem Halogenatom substituiert sein kann, eine substituierte Silylgruppe mit 1 bis 20 Kohlenstoffatomen, die mit einem Halogenatom substituiert sein kann, einen Alkoxyrest mit 1 bis 20 Kohlenstoffatomen, der mit einem Halogenatom substituiert sein kann, einen Aralkoxyrest mit 7 bis 20 Kohlenstoffatomen, der mit einem Halogenatom substituiert sein kann, einen Aryloxyrest mit 6 bis 20 Kohlenstoffatomen, der mit einem Halogenatom substituiert sein kann, oder eine disubstituierte Aminogruppe mit 2 bis 20 Kohlenstoffatomen darstellt, R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup> und R<sup>6</sup> gegebenenfalls jeweils miteinander kombiniert werden können, um einen Ring zu bilden).

11. Thermoplastische Harzzusammensetzung, umfassend 3 bis 95 Gewichts-%, vorzugsweise 10 bis 80 Gewichts-% Propylen-1-Buten-Copolymer gemäß Anspruch 1 und 97 bis 5 Gewichts-%, vorzugsweise 90 bis 20 Gewichts-% Polyolefinharz.

12. Thermoplastische Harzzusammensetzung gemäß Anspruch 11, bei der das Polyolefinharz ein kristallines Polypropylenharz ist.

13. Verwendung der thermoplastischen Harzzusammensetzung gemäß den Ansprüchen 11 oder 12 für die Herstellung von Formgegenständen.

#### Revendications

1. Copolymère propylène-1-butène dans lequel la dureté dans l'échelle Shore A mesurée conformément à la norme ASTM D2240 n'est pas supérieure à 70 et la viscosité intrinsèque  $[\eta]$  mesurée dans un solvant de xylène à la température de 70°C n'est pas inférieure à 0,3 et qui ne présente pas de pic de fusion cristalline et pas de pic de cristallisation au cours d'une mesure par calorimètre différentiel (DSC).


2. Copolymère propylène-1-butène selon la revendication 1, dans lequel la dureté dans l'échelle Shore A mesurée conformément à la norme ASTM D2240 n'est pas supérieure à 60.

3. Copolymère propylène-1-butène selon la revendication 1 ou 2, dans lequel la viscosité intrinsèque  $[\eta]$  mesurée dans un solvant de xylène à la température de 70°C n'est pas inférieure à 0,5.

4. Copolymère propylène-1-butène selon l'une quelconque des revendications 1 à 3, dans lequel le module de flexion de la composition de résine thermoplastique comprenant 50 % en poids du copolymère propylène-1-butène et 50 % en poids de l'homopolypropylène est inférieur à 2500 kgf/cm<sup>2</sup>.

5. Copolymère propylène-1-butène selon l'une quelconque des revendications 1 à 4, dans lequel la distribution des masses moléculaires Mw/Mn mesurée par chromatographie par perméation de gel (GPC) n'est pas supérieure à 3.

6. Copolymère propylène-1-butène selon l'une quelconque des revendications 1 à 5, dans lequel la teneur en 1-butène va de 0,5 à 90 % en moles, de préférence de 1 à 70 % en moles.
7. Copolymère propylène-1-butène selon l'une quelconque des revendications 1 à 6, dans lequel la teneur en composant insoluble dans le n-heptane bouillant n'est pas supérieure à 5 % en poids, de préférence pas supérieure à 3 % en poids.
8. Copolymère propylène-1-butène selon l'une quelconque des revendications 1 à 7, dans lequel la teneur en composant soluble dans l'acétate de méthyle bouillant n'est pas supérieure à 2 % en poids.
9. Copolymère propylène-1-butène selon l'une quelconque des revendications 1 à 8, dans lequel ledit copolymère est obtenu en copolymérisant du propylène avec du 1-butène en utilisant un catalyseur qui peut produire un polymère de propylène ne présentant ni un pic de fusion cristalline, ni un pic de cristallisation dans le cas d'une mesure par un calorimètre différentiel (DSC).
10. Copolymère propylène-1-butène selon la revendication 9, dans lequel le catalyseur est représenté par la formule chimique (I) suivante :



[ I ]

(dans laquelle M¹ représente un atome de métal de transition du groupe 4 du tableau périodique des éléments, A représente un atome du groupe 16 du tableau périodique des éléments, B représente un atome du groupe 14 du tableau périodique des éléments, Cp¹ représente un groupement présentant un squelette d'anion de la forme cyclopentadiène, X¹, X², R¹, R², R³, R⁴, R⁵ et R⁶ représentent indépendamment un atome d'hydrogène, un atome d'halogène, un groupement alkyle comportant 1 à 20 atomes de carbone qui peuvent être substitués par un atome d'halogène, un groupement aralkyle comportant 7 à 20 atomes de carbone qui peuvent être substitués par un atome d'halogène, un groupement aryle comportant 6 à 20 atomes de carbone qui peuvent être substitués par un atome d'halogène, un groupement silyle substitué comportant 1 à 20 atomes de carbone qui peuvent être substitués par un atome d'halogène, un groupement alcoxy comportant 1 à 20 atomes de carbone qui peuvent être substitués par un atome d'halogène, un groupement aralkyloxy comportant 7 à 20 atomes de carbone qui peuvent être substitués par un atome d'halogène, un groupement aryloxy comportant 6 à 20 atomes de carbone qui peuvent être substitués par un atome d'halogène, ou un groupement amino di-substitué comportant 2 à 20 atomes de carbone, R¹, R², R³, R⁴, R⁵ et R⁶ peuvent être facultativement combinés les uns avec les autres afin de former un cycle).

11. Composition de résine thermoplastique comprenant 3 à 95 % en poids, de façon préférable 10 à 80 % en poids du copolymère propylène-1-butène selon la revendication 1 et 97 à 5 % en poids, de façon préférable 90 à 20 % en poids d'une résine de polyoléfine.
12. Composition de résine thermoplastique selon la revendication 11, dans laquelle la résine de polyoléfine est une résine de polypropylène cristalline.
13. Utilisation de la composition de résine thermoplastique selon les revendications 11 ou 12 en vue de la fabrication d'articles formés.